

# TABELLA DI CONFRONTO FRA I MATERIALI

## ACCIAIO AL CARBONIO

Germania		Regno Unito		Francia	Italia	Spagna	Svezia	Giappone	USA	Cina
W.-nr.	DIN	BS	EN	AFNOR	UNI	UNE	SS	JIS	AISI/SAE	GB
1.0038	RSt.37-2	4360 40 C	-	E 24-2 Ne	-	-	1311	STKM 12A STKM 12C	A570.36	15
1.0401	C15	080M15	-	CC12	C15, C16	F.111	1350	-	1015	15
1.0402	C22	050A20	2C	CC20	C20, C21	F.112	1450	-	1020	20
1.0715	9SMn28	230M07	1A	S250	CF9SMn28	F.2111 11SMn28	1912	SUM22	1213	Y15
1.0718	9SMnPb28	-	-	S250Pb	CF9SMnPb28	11SMnPb28	1914	SUM22L	12L13	-
1.0722	10SPb20	-	-	10PbF2	CF10Pb20	10SPb20	-	-	-	-
1.0736	9SMn36	240M07	1B	S300	CF9SMn36	12SMn35	-	-	1215	Y13
1.0737	9SMnPb36	-	-	S300Pb	CF9SMnPb36	12SMnP35	1926	-	12L14	-
1.1141	Ck15	080M15	32C	XC12	C16	C15K	1370	S15C	1015	15
1.1158	Ck25	-	-	-	-	-	-	S25C	1025	25
1.8900	StE380	4360 55 E	-	-	FeE390KG	-	2145	-	A572-60	-
1.0501	C35	060A35	-	CC35	C35	F.113	1550	-	1035	35
1.0503	C45	080M46	-	CC45	C45	F.114	1650	-	1045	45
1.0726	35S20	212M36	8M	35MF4	-	F210G	1957	-	1140	-
1.1157	40Mn4	150M36	15	35M5	-	-	-	-	1039	40Mn
1.1167	36Mn5	-	-	40M5	-	36Mn5	2120	SMn438(H)	1335	35Mn2
1.1170	28Mn6	150M28	14A	20M5	C28Mn	-	-	SCMn1	1330	30Mn
1.1183	Cf35	060A35	-	XC38TS	C36	-	1572	S35C	1035	35Mn
1.1191	Ck45	080M46	-	XC42	C45	C45K	1672	S45C	1045	Ck45
1.1213	Cf53	060A52	-	XC48TS	C53	-	1674	S50C	1050	50
1.0535	C55	070M55	9	-	C55	-	1655	-	1055	55
1.0601	C60	080A62	43D	CC55	C60	-	-	-	1060	60
1.1203	Ck55	070M55	-	XC55	C50	C55K	-	S55C	1055	55
1.1221	Ck60	080A62	43D	XC60	C60	-	1678	S58C	1060	60Mn
1.1274	Ck101	060A96	-	XC100	-	F.5117	1870	-	1095	-
1.1545	C105W1	BW1A	-	Y105	C36KU	F.5118	1880	SK3	W1	-
1.1545	C105W1	BW2	-	Y120	C120KU	F.515	2900	SUP4	W210	-

## ACCIAIO LEGATO

Germania		Regno Unito		Francia	Italia	Spagna	Svezia	Giappone	USA	Cina
W.-nr.	DIN	BS	EN	AFNOR	UNI	UNE	SS	JIS	AISI/SAE	GB
1.0144	St.44.2	4360 43 C	-	E28-3	-	-	1412	SM400A, SM400B SM400C	A573-81	-
1.0570	St52-3	4360 50 B	-	E36-3	Fe52BFN Fe52CFN	-	2132	SM490A, SM490B SM490C	-	-
1.0841	St52-3	150M19	-	20MC5	Fe52	F.431	2172	-	5120	-
1.0904	55Si7	250A53	45	55S7	55Si8	56Si7	2085	-	9255	55Si2Mn
1.0961	60SiCr7	-	-	60SC7	60SiCr8	60SiCr8	-	-	9262	-
1.3505	100Cr6	534A99	31	100C6	100Cr6	F.131	2258	SUJ2	ASTM 52100	Gr15, 45G
1.5415	15Mo3	1501-240	-	15D3	16Mo3KW	16Mo3	2912	-	ASTM A204Gr.A	-
1.5423	16Mo5	1503-245-420	-	-	16Mo5	16Mo5	-	-	4520	-
1.5622	14Ni6	-	-	16N6	14Ni6	15Ni6	-	-	ASTM A350LF5	-
1.5662	X8Ni9	1501-509-510	-	-	X10Ni9	XBNI09	-	-	ASTM A353	-
1.5710	36NiCr6	640A35	111A	35NC6	-	-	-	SNC236	3135	-
1.5732	14NiCr10	-	-	14NC11	16NiCr11	15NiCr11	-	SNC415(H)	3415	-
1.5752	14NiCr14	655M13	36A	12NC15	-	-	-	SNC815(H)	3415, 3310	-
1.6523	21NiCrMo2	805M20	362	20NCD2	20NiCrMo2	20NiCrMo2	2506	SNCM220(H)	8620	-
1.6546	40NiCrMo22	311-Type 7	-	-	40NiCrMo2(KB)	40NiCrMo2	-	SNCM240	8740	-
1.6587	17CrNiMo6	820A16	-	18NCD6	-	14NiCrMo13	-	-	-	-
1.7015	15Cr3	523M15	-	12C3	-	-	-	SCr415(H)	5015	15Cr

Germania		Regno Unito		Francia	Italia	Spagna	Svezia	Giappone	USA	Cina
W.-nr.	DIN	BS	EN	AFNOR	UNI	UNE	SS	JIS	AISI/SAE	GB
1.7045	42Cr4	–	–	–	–	42Cr4	2245	SCr440	5140	40Cr
1.7176	55Cr3	527A60	48	55C3	–	–	–	SUP9(A)	5155	20CrMn
1.7262	15CrMo5	–	–	12CD4	–	12CrMo4	2216	SCM415(H)	–	–
1.7335	13CrMo4 4	1501-620Gr27	–	15CD3.5 15CD4.5	14CrMo45	14CrMo45	–	–	ASTM A182 F11, F12	–
1.7380	10CrMo910	1501-622 Gr31, 45	–	12CD9 12CD10	12CrMo9 12CrMo10	TU.H	2218	–	ASTM A182 F.22	–
1.7715	14MoV63	1503-660-440	–	–	–	13MoCrV6	–	–	–	–
1.8523	39CrMoV13 9	897M39	40C	–	36CrMoV12	–	–	–	–	–
1.6511	36CrNiMo4	816M40	110	40NCD3	38NiCrMo4(KB)	35NiCrMo4	–	–	9840	–
1.6582	34CrNiMo6	817M40	24	35NCD6	35NiCrMo6(KB)	–	2541	–	4340	40CrNiMoA
1.7033	34Cr4	530A32	18B	32C4	34Cr4(KB)	35Cr4	–	SCr430(H)	5132	35Cr
1.7035	41Cr4	530M40	18	42C4	41Cr4	42Cr4	–	SCr440(H)	5140	40Cr
1.7131	16MnCr5	(527M20)	–	16MC5	16MnCr5	16MnCr5	2511	–	5115	18CrMn
1.7218	25CrMo4	1717CDS110 708M20	–	25CD4	25CrMo4(KB)	55Cr3	2225	SCM420 SCM430	4130	30CrMn
1.7220	34CrMo4	708A37	19B	35CD4	35CrMo4	34CrMo4	2234	SCM432 SCCRM3	4137 4135	35CrMo
1.7223	41CrMo4	708M40	19A	42CD4TS	41CrMo4	42CrMo4	2244	SCM 440	4140 4142	40CrMoA
1.7225	42CrMo4	708M40	19A	42CD4	42CrMo4	42CrMo4	2244	SCM440(H)	4140	42CrMo 42CrMnMo
1.7361	32CrMo12	722M24	40B	30CD12	32CrMo12	F.124.A	2240	–	–	–
1.8159	50CrV4	735A50	47	50CV4	50CrV4	51CrV4	2230	SUP10	6150	50CrVA
1.8509	41CrAlMo7	905M39	41B	40CAD6 40CAD2	41CrAlMo7	41CrAlMo7	2940	–	–	–
1.2067	100Cr6	BL3	–	Y100C6	–	100Cr6	–	–	L3	CrV, 9SiCr
1.2419	105WCr6	–	–	105WC13	100WCr6 107WCr5KU	105WCr5	2140	SKS31 SKS2, SKS3	–	CrWMo
1.2713	55NiCrMoV6	BH224/5	–	55NCDV7	–	F.520.S	–	SKT4	L6	5CrNiMo
1.5662	X8Ni9	1501-509	–	–	X10Ni9	XBNI09	–	–	ASTM A353	–
1.5680	12Ni19	–	–	Z18N5	–	–	–	–	2515	–
1.6657	14NiCrMo134	832M13	36C	–	15NiCrMo13	14NiCrMo131	–	–	–	–
1.2080	X210Cr12	BD3	–	Z200C12	X210Cr13KU X250Cr12KU	X210Cr12	–	SKD1	D3 ASTM D3	Cr12
1.2344	X40CrMoV51 X40CrMoV51	BH13	–	Z40CDV5	X35CrMoV05KU X40CrMoV51KU	X40CrMoV5	2242	SKD61	H13 ASTM H13	40CrMoV5
1.2363	X100CrMoV51	BA2	–	Z100CDV5	X100CrMoV51KU	X100CrMoV5	2260	SKD12	A2	100CrMoV5
1.2436	X210CrW12	–	–	–	X215CrW121KU	X210CrW12	2312	SKD2	–	–
1.2542	45WCrV7	BS1	–	–	45WCrV8KU	45WCrSi8	2710	–	S1	–
1.2581	X30WCrV93	BH21	–	Z30WCV9	X28W09KU	X30WCrV9	–	SKD5	H21	30WCrV9
1.2601	X165CrMoV12	–	–	–	X165CrMoV12KU	X160CrMoV12	2310	–	–	–
1.2833	100V1	BW2	–	Y1105V	–	–	–	SKS43	W210	V
1.3255	S 18-1-2-5	BT4	–	Z80WKCV	X78WCo1805KU	HS18-1-1-5	–	SKH3	T4	W18Cr4VCo5
1.3355	S 18-0-1	BT1	–	Z80WCV	X75W18KU	HS18-0-1	–	SKH2	T1	–
1.3401	G-X120Mn12	Z120M12	–	Z120M12	XG120Mn12	X120MN12	–	SCMnH/1	–	–
1.4718	X45CrSi93	401S45	52	Z45CS9	X45CrSi8	F.322	–	SUH1	HW3	X45CrSi93
1.3343	S6-5-2	4959BA2	–	Z40CSD10	15NiCrMo13	–	2715	SUH3	D3	–
1.3343	S6/5/2	BM2	–	Z85WDCV	HS6-5-2-2	F.5603	2722	SKH9, SKH51	M2	–
1.3348	S 2-9-2	–	–	–	HS2-9-2	HS2-9-2	2782	–	M7	–
1.3243	S6/5/2/5	BM35	–	6-5-2-5	HS6-5-2-5	F.5613	2723	SKH55	M35	–

# TABELLA DI CONFRONTO FRA I MATERIALI

## ACCIAIO INOSSIDABILE (FERRITICO,MARTENSITICO)

Germania		Regno Unito		Francia	Italia	Spagna	Svezia	Giappone	USA	Cina
W.-nr.	DIN	BS	EN	AFNOR	UNI	UNE	SS	JIS	AISI/SAE	GB
1.4000	X7Cr13	403S17	-	Z6C13	X6Cr13	F.3110	2301	SUS403	403	OCr13 1Cr12
1.4001	X7Cr14	-	-	-	-	F.8401	-	-	-	-
1.4005	X12CrS13	416S21	-	Z11CF13	X12CrS13	F.3411	2380	SUS416	416	-
1.4006	X10Cr13	410S21	56A	Z10C14	X12Cr13	F.3401	2302	SUS410	410	1Cr13
1.4016	X8Cr17	430S15	60	Z8C17	X8Cr17	F.3113	2320	SUS430	430	1Cr17
1.4027	G-X20Cr14	420C29	56B	Z20C13M	-	-	-	SCS2	-	-
1.4034	X46Cr13	420S45	56D	Z40CM Z38C13M	X40Cr14	F.3405	2304	SUS420J2	-	4Cr13
1.4003	-	405S17	-	Z8CA12	X6CrAl13	-	-	-	405	-
1.4021	-	420S37	-	Z8CA12	X20Cr13	-	2303	-	420	-
1.4057	X22CrNi17	431S29	57	Z15CNi6.02	X16CrNi16	F.3427	2321	SUS431	431	1Cr17Ni2
1.4104	X12CrMoS17	-	-	Z10CF17	X10CrS17	F.3117	2383	SUS430F	430F	Y1Cr17
1.4113	X6CrMo17	434S17	-	Z8CD17.01	X8CrMo17	-	2325	SUS434	434	1Cr17Mo
1.4313	X5CrNi134	425C11	-	Z4CND13.4M	(G)X6CrNi304	-	2385	SCS5	CA6-NM	-
1.4724	X10CrA113	403S17	-	Z10C13	X10CrA112	F.311	-	SUS405	405	OCr13Al
1.4742	X10CrA118	430S15	60	Z10CAS18	X8Cr17	F.3113	-	SUS430	430	Cr17
1.4747	X80CrNiSi20	443S65	59	Z80CSN20.02	X80CrSiNi20	F.320B	-	SUH4	HNV6	-
1.4762	X10CrA124	-	-	Z10CAS24	X16Cr26	-	2322	SUH446	446	2Cr25N
1.4871	X53CrMnNiN219	349S54	-	Z52CMN21.09	X53CrMnNiN219	-	-	SUH35	EV8	5Cr2Mn9Ni4N
1.4521	X1CrMoTi182	-	-	-	-	-	2326	-	S44400	-
1.4922	X20CrMoV12-1	-	-	-	X20CrMoNi1201	-	2317	-	-	-
1.4542	-	-	-	Z7CNU17-04	-	-	-	-	630	-

## ACCIAIO INOSSIDABILE (AUSTENITICO)

Germania		Regno Unito		Francia	Italia	Spagna	Svezia	Giappone	USA	Cina
W.-nr.	DIN	BS	EN	AFNOR	UNI	UNE	SS	JIS	AISI/SAE	GB
1.4306	X2CrNi1911	304S11	-	Z2CN18.10	X2CrNi18.11	-	2352	SUS304L	304L	OCr19Ni10
1.4350	X5CrNi189	304S11	58E	Z6CN18.09	X5CrNi1810	F.3551 F.3541 F.3504	2332	SUS304	304	OCr18Ni9
1.4305	X12CrNiS188	303S21	58M	Z10CNF18.09	X10CrNiS18.09	F.3508	2346	SUS303	303	1Cr18Ni9MoZr
-	-	304C12	-	Z3CN19.10	-	-	2333	SUS304L	-	-
1.4306	X2CrNi189	304S12	-	Z2CrNi1810	X2CrNi18.11	F.3503	2352	SCS19	304L	-
1.4310	X12CrNi177	-	-	Z12CN17.07	X12CrNi1707	F.3517	2331	SUS301	301	Cr17Ni7
1.4311	X2CrNiN1810	304S62	-	Z2CN18.10	-	-	2371	SUS304LN	304LN	-
1.4401	X5CrNiMo1810	316S16	58J	Z6CND17.11	X5CrNiMo1712	F.3543	2347	SUS316	316	OCr17Ni11Mo2
1.4308	G-X6CrNi189	304C15	-	Z6CN18.10M	-	-	-	SCS13	-	-
1.4408	G-X6CrNiMo1810	316C16	-	-	-	F.8414	-	SCS14	-	-
1.4581	G-X5CrNiMoNb1810	318C17	-	Z4CNDNb1812M	XG8CrNiMo1811	-	-	SCS22	-	-
1.4429	X2CrNiMoN1813	-	-	Z2CND17.13	-	-	2375	SUS316LN	316LN	OCr17Ni13Mo
1.4404	-	316S13	-	Z2CND17.12	X2CrNiMo1712	-	2348	-	316L	-
1.4435	X2CrNiMo1812	316S13	-	Z2CND17.12	X2CrNiMo1712	-	2353	SCS16 SUS316L	316L	OCr27Ni12Mo3
1.4436	-	316S13	-	Z6CND18-12-03	X8CrNiMo1713	-	2343, 2347	-	316	-
1.4438	X2CrNiMo1816	317S12	-	Z2CND19.15	X2CrNiMo1816	-	2367	SUS317L	317L	OCr19Ni13Mo
1.4539	X1NiCrMo	-	-	Z6CNT18.10	-	-	2562	-	UNS V 0890A	-
1.4541	X10CrNiTi189	321S12	58B	Z6CNT18.10	X6CrNiTi1811	F.3553 F.3523	2337	SUS321	321	1Cr18Ni9Ti
1.4550	X10CrNiNb189	347S17	58F	Z6CNNb18.10	X6CrNiNb1811	F.3552 F.3524	2338	SUS347	347	1Cr18Ni11Nb
1.4571	X10CrNiMoTi1810	320S17	58J	Z6CNDT17.12	X6CrNiMoTi1712	F.3535	2350	-	316Ti	Cr18Ni12Mo2T
1.4583	X10CrNiMoNb1812	-	-	Z6CNDNb1713B	X6CrNiMoNb1713	-	-	-	318	Cr17Ni12Mo3Mb

Germania		Regno Unito		Francia	Italia	Spagna	Svezia	Giappone	USA	Cina
W.-nr.	DIN	BS	EN	AFNOR	UNI	UNE	SS	JIS	AISI/SAE	GB
1.4828	X15CrNiSi2012	309S24	–	Z15CNS20.12	X6CrNi2520	–	–	SUH309	309	1Cr23Ni13
1.4845	X12CrNi2521	310S24	–	Z12CN2520	X6CrNi2520	F.331	2361	SUH310	310S	OCr25Ni20
1.4406	X10CrNi18.08	–	58C	Z1NCNDU25.20	–	F.8414	2370	SCS17	308	–
1.4418	X4CrNiMo165	–	–	Z6CND16-04-01	–	–	–	–	–	–
1.4568	–	316S111	–	Z8CNA17-07	X2CrNiMo1712	–	–	–	17-7PH	–
1.4504	–	–	–	–	–	–	–	–	–	–
1.4563	–	–	–	Z1NCNDU31-27-03 Z1CNDU20-18-06AZ	–	–	2584 2378	–	NO8028 S31254	–
1.4878	X12CrNiTi189	321S32	58B, 58C	Z6CNT18.12B	X6CrNiTi18 11	F.3523	–	SUS321	321	1Cr18Ni9Ti

## ACCIAI RESISTENTI AL CALORE

Germania		Regno Unito		Francia	Italia	Spagna	Svezia	Giappone	USA	Cina
W.-nr.	DIN	BS	EN	AFNOR	UNI	UNE	SS	JIS	AISI/SAE	GB
1.4864	X12NiCrSi3616	–	–	Z12NCS35.16	–	–	–	SUH330	330	–
1.4865	G-X40NiCrSi3818	330C11	–	–	XG50NiCr3919	–	–	SCH15	HT, HT 50	–

## GHISA GRIGIA

Germania		Regno Unito		Francia	Italia	Spagna	Svezia	Giappone	USA	Cina
W.-nr.	DIN	BS	EN	AFNOR	UNI	UNE	SS	JIS	AISI/SAE	GB
–	–	–	–	–	–	–	0100	–	–	–
–	GG 10	–	–	Ft 10 D	–	–	0110	FC100	No 20 B	–
0.6015	GG 15	Grade 150	–	Ft 15 D	G15	FG15	0115	FC150	No 25 B	HT150
0.6020	GG 20	Grade 220	–	Ft 20 D	G20	–	0120	FC200	No 30 B	HT200
0.6025	GG 25	Grade 260	–	Ft 25 D	G25	FG25	0125	FC250	No 35 B	HT250
–	–	–	–	–	–	–	–	–	No 40 B	–
0.6030	GG 30	Grade 300	–	Ft 30 D	G30	FG30	0130	FC300	No 45 B	HT300
0.6035	GG 35	Grade 350	–	Ft 35 D	G35	FG35	0135	FC350	No 50 B	HT350
0.6040	GG 40	Grade 400	–	Ft 40 D	–	–	0140	–	No 55 B	HT400
0.6660	GGL NiCr202	L-NiCuCr202	–	L-NC 202	–	–	0523	–	A436 Type 2	–

## GHISA SFEROIDALE

Germania		Regno Unito		Francia	Italia	Spagna	Svezia	Giappone	USA	Cina
W.-nr.	DIN	BS	EN	AFNOR	UNI	UNE	SS	JIS	AISI/SAE	GB
0.7040	GGG 40	SNG 420/12	–	FCS 400-12	GS 370-17	FGE 38-17	07 17-02	FCD400	60-40-18	QT400-18
–	GGG 40.3	SNG 370/17	–	FGS 370-17	–	–	07 17-12	–	–	–
0.7033	GGG 35.3	–	–	–	–	–	07 17-15	–	–	–
0.7050	GGG 50	SNG 500/7	–	FGS 500-7	GS 500	FGE 50-7	07 27-02	FCD500	80-55-06	QT500-7
0.7660	GGG NiCr202	Grade S6	–	S-NC202	–	–	07 76	–	A43D2	–
–	GGG NiMn137	L-NiMn 137	–	L-MN 137	–	–	07 72	–	–	–
–	GGG 60	SNG 600/3	–	FGS 600-3	–	–	07 32-03	FCD600	–	QT600-3
0.7070	GGG 70	SNG 700/2	–	FGS 700-2	GS 700-2	FGS 70-2	07 37-01	FCD700	100-70-03	QT700-18

## GHISA MALLEABILE

Germania		Regno Unito		Francia	Italia	Spagna	Svezia	Giappone	USA	Cina
W.-nr.	DIN	BS	EN	AFNOR	UNI	UNE	SS	JIS	AISI/SAE	GB
–	–	8 290/6	–	MN 32-8	–	–	08 14	FCMB310	–	–
–	GTS-35	B 340/12	–	MN 35-10	–	–	08 15	FCMW330	32510	–
0.8145	GTS-45	P 440/7	–	Mn 450	GMN45	–	08 52	FCMW370	40010	–
0.8155	GTS-55	P 510/4	–	MP 50-5	GMN55	–	08 54	FCMP490	50005	–
–	GTS-65	P 570/3	–	MP 60-3	–	–	08 58	FCMP540	70003	–
0.8165	GTS-65-02	P 570/3	–	Mn 650-3	GMN 65	–	08 56	FCMP590	A220-70003	–
–	GTS-70-02	P 690/2	–	Mn 700-2	GMN 70	–	08 62	FCMP690	A220-80002	–